



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07F 7/00, C08F 4/60, 10/00		A1	(11) International Publication Number: WO 99/01460
			(43) International Publication Date: 14 January 1999 (14.01.99)
(21) International Application Number: PCT/US98/13781		(81) Designated States: AU, BR, CA, CN, CZ, HU, ID, JP, KR, MX, PL, SG, SK, TR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 1 July 1998 (01.07.98)		Published With international search report.	
(30) Priority Data: 60/051,581 2 July 1997 (02.07.97) US			
(71) Applicant: UNION CARBIDE CHEMICALS & PLASTICS TECHNOLOGY CORPORATION [US/US]; 39 Old Ridgebury Road, Danbury, CT 06817-0001 (US).			
(72) Inventor: MURRAY, Rex, Eugene; Apartment 522, 5291 Dalewood Drive, Charleston, WV 25313 (US).			
(74) Agent: WIGGINS, Karen, Johnson; Union Carbide Chemicals & Plastics Technology Corporation, 39 Old Ridgebury Road, Danbury, CT 06817-0001 (US).			
(54) Title: CATALYST FOR THE PRODUCTION OF OLEFIN POLYMERS			
(57) Abstract			
<p>A catalyst precursor having the formula: $A_q M L_n$ wherein each A has formula (I); M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements; each L is a monovalent, bivalent, or trivalent anion; X and Y are each heteroatoms; Cyclo is a cyclic moiety; each R^1 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety; each R^2 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety; Q is a bridging group; each m is independently an integer from 0 to 5; n is an integer from 1 to 4; q is 1 or 2; and when q is 2, the A groups are optionally connected by a bridging group Z is provided. The catalyst precursor may be made by reacting an organometal compound with a heteroatom-containing ligand. The catalyst precursor, when combined with an activating cocatalyst, is useful for the polymerization of olefins.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

-1-

CATALYST FOR THE PRODUCTION OF OLEFIN POLYMERS

This application claims the benefit of provisional U.S. Application Serial No. 60/051,581, filed 7/2/97, the disclosure of which is incorporated herein by reference.


The invention relates to a family of novel heteroatom-containing catalyst precursors useful for the polymerization of olefins, such as ethylene, higher alpha-olefins, dienes, and mixtures thereof.

BACKGROUND


A variety of metallocenes and other single site-like catalysts have been developed to prepare olefin polymers. Metallocenes are organometallic coordination complexes containing one or more π -bonded moieties (i.e., cyclopentadienyl groups) in association with a metal atom. Catalyst compositions containing metallocenes and other single site-like catalysts are highly useful in the preparation of polyolefins, producing relatively homogeneous copolymers at excellent polymerization rates while allowing one to tailor closely the final properties of the polymer as desired.

Recently, work relating to certain nitrogen-containing, single site-like catalyst precursors has been published. PCT Application No. WO 96/23101 relates to di(imine) metal complexes that are transition metal complexes of bidentate ligands selected from the group consisting of:


-2-




(V)



(VI)



(VII), and



(VIII)

wherein said transition metal is selected from the group consisting of Ti, Zr, Sc, V, Cr, a rare earth metal, Fe, Co, Ni, and Pd;

-3-

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

R⁴⁴ is hydrocarbyl or substituted hydrocarbyl, and R²⁸ is hydrogen, hydrocarbyl or substituted hydrocarbyl or R⁴⁴ and R²⁸ taken together form a ring;

R⁴⁵ is hydrocarbyl or substituted hydrocarbyl, and R²⁹ is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R⁴⁵ and R²⁹ taken together form a ring;

each R³⁰ is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R³⁰ taken together form a ring;

each R³¹ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

R⁴⁶ and R⁴⁷ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R⁴⁸ and R⁴⁹ are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

R²⁰ and R²³ are independently hydrocarbyl or substituted hydrocarbyl;

R²¹ and R²² are independently hydrogen, hydrocarbyl or substituted hydrocarbyl; and

n is 2 or 3;

-4-





and provided that:

said transition metal also has bonded to it a ligand that may be displaced by or added to the olefin monomer being polymerized; and









when the transition metal is Pd, said bidentate ligand is (V), (VII) or (VIII).

Similarly, PCT Application No. WO 97/02298 relates to a process for the polymerization of an olefin, comprising contacting a polymerizable monomer consisting essentially of ethylene, a norbornene or a styrene, with a catalyst system comprising the product of mixing in solution a zerovalent tricoordinate or tetracoordinate nickel compound (II) which has at least one labile ligand, and all ligands are neutral, an acid of the formula HX (IV), and a first compound selected from the group consisting of:



Ar^1Q_n (III); $\text{R}^8\text{R}^{10}\text{N}-\text{CR}^4\text{R}^5(\text{CR}^6\text{R}^7)_m-\text{NR}^8\text{R}^{10}$ (V);



-5-



-6-



wherein:

X is a noncoordinating anion;

Ar¹ is an aromatic moiety with n free valencies, or diphenylmethyl;

each Q is -NR²R⁴³ or -CR⁹=NR³;

R⁴³ is hydrogen or alkyl;

n is 1 or 2;

E is 2-thienyl or 2-furyl;

each R² is independently hydrogen, benzyl, substituted benzyl, phenyl or substituted phenyl;

each R⁹ is independently hydrogen or hydrocarbyl; and

each R³ is independently a monovalent aromatic moiety;

m is 1, 2 or 3;

each R⁴, R⁵, R⁶, and R⁷ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

each R⁸ is independently hydrocarbyl or substituted hydrocarbyl containing 2 or more carbon atoms;

each R¹⁰ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

-7-

Ar² is an aryl moiety;

R¹², R¹³, and R¹⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group;

R¹¹ and R¹⁵ are each independently hydrocarbyl, substituted hydrocarbyl or an inert functional group whose E_S is about -0.4 or less;

each R¹⁶ and R¹⁷ is independently hydrogen or acyl containing 1 to 20 carbon atoms;

Ar³ is an aryl moiety;

R¹⁸ and R¹⁹ are each independently hydrogen or hydrocarbyl;

Ar⁴ is an aryl moiety;

Ar⁵ and Ar⁶ are each independently hydrocarbyl;

Ar⁷ and Ar⁸ are each independently an aryl moiety;

Ar⁹ and Ar¹⁰ are each independently an aryl moiety or -CO₂R²⁵, wherein R²⁵ is alkyl containing 1 to 20 carbon atoms;

Ar¹¹ is an aryl moiety;

R⁴¹ is hydrogen or hydrocarbyl;

R⁴² is hydrocarbyl or -C(O)-NR⁴¹-Ar¹¹;


R⁴⁴ is aryl;

R²² and R²³ are each independently phenyl groups substituted by one or more alkoxy groups, each alkoxy group containing 1 to 20 carbon atoms; and

R²⁴ is alkyl containing 1 to 20 carbon atoms, or an aryl moiety.

-8-

PCT Application No. WO 96/33202 relates to a transition metal catalyst containing a pyridine or quinoline moiety and having the formula:




where Y is O, S, NR-, $\left[\begin{array}{c} R \\ | \\ C \\ | \\ R_n \end{array} \right]$ -NR-, or $\left[\begin{array}{c} R \\ | \\ C \\ | \\ R_n \end{array} \right]$ -O-,

each R is independently selected from hydrogen or C₁ to C₆ alkyl, each R' is independently selected from C₁ to C₆ alkyl, C₁ to C₆ alkoxy, C₆ to C₁₆ aryl, halogen, or CF₃, M is titanium, zirconium, or hafnium, each X is independently selected from halogen, C₁ to C₆ alkyl, C₁ to C₆ alkoxy, or


$\begin{array}{c} R \\ \diagup \\ -N \\ \diagdown \\ R \end{array}$, L is X, cyclopentadienyl, C₁ to C₆ alkyl substituted cyclopentadienyl, indenyl, fluorenyl, or

-9-



, "m" is 0 to 4, and "n" is 1 to 4.

Similarly, Fuhrmann et al., *Inorg. Chem.*, 35:6742-6745 (1996) discloses certain Group 4 metal complexes containing amine, amido, and aminopyridinato ligands such as:




wherein TMS is trimethylsilyl.

An olefin polymerization catalyst composition is described herein having good polymerization activity and productivity. The catalyst composition comprises a heteroatom-containing catalyst precursor having the formula:



wherein each A has the formula:



-10-

M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements;

each L is a monovalent, bivalent, or trivalent anion;

X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R¹ is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R¹ groups may be joined to form a cyclic moiety;

each R² is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R² groups may be joined to form a cyclic moiety;

Q is a bridging group;

each m is independently an integer from 0 to 5;


n is an integer from 1 to 4;

q is 1 or 2;

and when q is 2, the A groups are optionally connected by a bridging group Z.

The catalyst precursor may be conveniently prepared by reacting an organometal compound with a heteroatom-containing ligand of the formula:

-11-




wherein X, Y, Q, Cyclo, R^1 , R^2 , and m have the meanings stated above.

SUMMARY OF THE INVENTION

The invention provides a catalyst precursor of the formula:



wherein each A has the formula:



M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements;

each L is a monovalent, bivalent, or trivalent anion;

X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

-12-

each R^1 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group;


each m is independently an integer from 0 to 5;

n is an integer from 1 to 4;

q is 1 or 2;

and when q is 2, the A groups are optionally connected by a bridging group Z; along with a catalyst composition comprising this catalyst precursor and an activating cocatalyst, as well as a process for the polymerization of olefins, using this catalyst composition.

The invention also provides a catalyst precursor comprising the reaction product of an organometal compound and heteroatom-containing ligand having a formula selected from the group consisting of:



-13-

wherein X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group; and


each m is independently an integer from 0 to 5; as well as a catalyst composition comprising this catalyst precursor and an activating cocatalyst, and a process for polymerizing olefins using this catalyst composition.

DETAILED DESCRIPTION OF THE INVENTION

The catalyst precursor may have the formula:



In the above formula, each A has the formula:



-14-

M is a metal selected from the group consisting of Group 3 to 13 and Lanthanide series elements, preferably a Group 4 element, more preferably zirconium.

Each L is a monovalent, bivalent, or trivalent anion, preferably independently selected from the group consisting of halogens; hydrogen; alkyl, aryl, alkenyl, alkylaryl, arylalkyl, hydrocarboxy radicals having 1-50 carbon atoms; amides; phosphides; sulfides; silylalkyls; diketonates; and carboxylates. More preferably, each L is selected from the group consisting of halides, alkyl radicals, and arylalkyl radicals. Most preferably, each L is selected from the group consisting of arylalkyl radicals such as benzyl. Each L may contain one or more heteroatoms.

X and Y are each heteroatoms and are preferably independently selected from the group consisting of N, O, S, and P. More preferably, X and Y are independently selected from the group consisting of N and P. Most preferably, X and Y are both nitrogen.

Y is contained in a heterocyclic ring containing 2 to 7 carbon atoms, preferably 3 to 6 carbon atoms, more preferably 5 carbon atoms. The heterocyclic ring may contain additional heteroatoms (i.e., in addition to Y).

Cyclo is a cyclic moiety. Preferably, Cyclo is a carbocyclic ring containing 3 to 7 carbon atoms. More preferably, Cyclo is an aryl group.

Each R¹ is independently a group containing 1 to 50 carbon atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R¹ groups may be joined to form a cyclic moiety such as an aliphatic or aromatic ring. Preferably, R¹ is an alkyl. More preferably, R¹ is isopropyl. Optionally, an R¹

-15-

group may be joined to Q. It is preferred that at least one R¹ is ortho to X.


Each R² is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R² groups may be joined to form a cyclic moiety such as an aliphatic or aromatic ring. Preferably, R² is hydrogen or an aryl. More preferably, R² is hydrogen. When R² is an aryl group and Y is N a quinoline group may be formed. Optionally, an R² group may be joined to Q.

Q is a bridging group. Preferably, Q contains one or more Group 13, 14, 15, or 16 elements. More preferably, Q contains one or more Group 14 elements. Most preferably, Q is a substituted carbon.

Each m is independently an integer from 0 to 5, preferably 2, and n is an integer from 1 to 4, preferably 3.

The letter q is 1 or 2, and when q is 2 the A groups are optionally connected by a bridging group Z. When present, Z preferably contains one or more Group IIIA, Group IVA, Group VA, or Group VIA elements. More preferably, Z contains one or more Group IVA elements.


In one embodiment of the invention, the catalyst precursor has the formula:



-16-


wherein R_a and R_b are each independently selected from the group consisting of alkyl, aryl, heterocyclic groups, and hydrogen; R_c and R_d are each independently selected from the group consisting of alkyl, aryl, and hydrogen; and each L has the meaning stated above.

In another embodiment of the invention, the catalyst precursor has the formula:



wherein R_a , R_b , R_c , R_d , and L have the meanings stated above.


In yet another embodiment of the invention, the catalyst precursor has the formula:



wherein R_a , R_b , R_c , R_d , and L have the meanings stated above.


In a further embodiment of the invention, the catalyst precursor has the formula:

-17-



wherein R_a , R_b , R_c , R_d , and L have the meanings stated above.


In a particularly preferred embodiment of the invention, the catalyst precursor has the formula:



Compound 1


In another particularly preferred embodiment of the invention, the catalyst precursor has the formula:

-18-




Compound 2

In further particularly preferred embodiment of the invention,
the catalyst precursor has the formula:



Compound 3


Yet another preferred catalyst precursor is:



Compound 4

-19-


The catalyst precursor may be made by any method. The method of making the catalyst precursor is not critical to the invention. However, one useful method of making the catalyst precursor is by reacting an organometal compound or a metal halide with a heteroatom-containing ligand having a formula selected from the group consisting of:



wherein X, Y, Q, Cyclo, R¹, R², and m have the meanings stated above.

Preferably, the catalyst precursor is made by reacting an organometal compound with the heteroatom-containing ligand. Accordingly, in one embodiment of the invention, the catalyst precursor comprises the reaction product of an organometal compound and a heteroatom-containing ligand having a formula selected from the group consisting of:

-20-



wherein X, Y, Q, Cyclo, R¹, R², and m have the meanings stated above.

The metal of the organometal compound may be selected from Group 3 to 13 elements and Lanthanide series elements. Preferably, the metal is a Group 4 element. More preferably the metal is zirconium.

The organometal compound for example may be a metal hydrocarbyl such as a metal alkyl, metal aryl, or metal arylalkyl. Metal silylalkyls, metal amides, or metal phosphides may also be used. Preferably, the organometal compound is a zirconium hydrocarbyl. More preferably, the organometal compound is a zirconium arylalkyl. Most preferably, the organometal compound is tetrabenzylzirconium.

Examples of useful organometal compounds are tetramethylzirconium, tetraethylzirconium, tetrakis[trimethylsilylmethyl]zirconium, tetrakis[dimethylamino]zirconium, dichlorodibenzylzirconium, chlorotribenzylzirconium, trichlorobenzylzirconium, bis[dimethylamino]bis[benzyl]zirconium, and tetrabenzylzirconium.

Tetramethyltitanium, tetraethyltitanium, tetrakis[trimethylsilylmethyl]titanium, tetrakis[dimethylamino]titanium, dichlorodibenzyltitanium,

-21-


chlorotribenzyltitanium, trichlorobenzyltitanium,
bis[dimethylamino]bis[benzyl]titanium, and tetrabenzyltitanium.

Tetramethylhafnium, tetraethylhafnium,
tetrakis[trimethylsilylmethyl]hafnium,
tetrakis[dimethylamino]hafnium, dichlorodibenzylhafnium,
chlorotribenzylhafnium, trichlorobenzylhafnium,
bis[dimethylamino]bis[benzyl]hafnium, and tetrabenzylhafnium.

Tetrakis[tertbutyl]lanthanates; lithiumhexamethylanthanates;
tetrakis[allyl]lanthanates; and
tris[bis[trimethylsilyl]methyl]lanthanides.

Because organometal compounds containing lanthanides and some transition metals are often difficult to prepare, it is preferred to prepare catalyst precursors containing these in a two-step process by first reacting the heteroatom-containing ligand with a lithium alkyl to make a lithium amide, and then reacting with a lanthanide or transition metal halide to generate the amide complex.


The heteroatom-containing ligand has the formula:




wherein X, Y, Q, Cyclo, R¹, R², and m have the meanings stated above.

Preferably, the heteroatom-containing ligand has the formula:

-22-



More preferably, the heteroatom-containing ligand is a pyridine/imine ligand of the formula:




wherein each R' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R' groups may be joined to form an aliphatic or aromatic ring;

each R'' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R'' groups may be joined to form an aliphatic or aromatic ring; and

R^3 is hydrogen, a hydrocarbon group containing 1 to 20 carbon atoms optionally substituted with one or more heteroatoms, or a heteroatom optionally substituted with a hydrocarbon group.

For example, Compound 1 may be made by reacting a substituted pyridine/imine ligand with a zirconium aryl such as tetrabenzyl zirconium:


-23-



This reaction is preferably carried out in a suitable solvent such as toluene or benzene at a temperature in the range of -50 to 50°C and a pressure ranging from a vacuum to 1000 psi.

Alternatively and preferably, the catalyst precursor can be made by reacting the heteroatom-containing ligand with a metal halide and then further reacting the product thereof with a Grignard reagent, such as an organomagnesium halide. For instance, the same catalyst precursor, Compound 1, may be made by reacting a substituted pyridine/imine ligand with a zirconium halide such as zirconium tetrachloride, and then further reacting the product thereof with PhCH_2MgCl .


Another preferred catalyst precursor, Compound 2, may be made by reacting a substituted pyridine/amine ligand with a zirconium aryl such as tetrabenzyl zirconium:



-24-


This reaction is preferably carried out in a suitable solvent such as toluene or benzene at a temperature in the range of -50 to 50°C and a pressure ranging from a vacuum to 1000 psi.

Another preferred catalyst precursor, Compound 3, may be made by reacting Compound 2 with acetone:



As another example, Compound 4 may be made in a multistep procedure by reacting a substituted pyridine/amine ligand sequentially with methyl lithium, chlorotrimethylsilane, zirconium tetrachloride, and benzyl magnesium chloride as follows:

-25-



This reaction is preferably carried out in a suitable solvent such as toluene or benzene at a temperature in the range of -50 to 50°C and a pressure ranging from a vacuum to 1000 psi.

The catalyst precursor may be isolated by conventional methods.


The catalyst composition comprises the catalyst precursor and an activating cocatalyst. The activating cocatalyst is capable of activating the catalyst precursor. Preferably, the activating cocatalyst is one of the following: (a) branched or cyclic oligomeric poly(hydrocarbylaluminum oxide)s which contain repeating units of the general formula $-(Al(R^*)O)-$, where R^* is hydrogen, an alkyl radical containing from 1 to about 12 carbon atoms, or an aryl radical such as a substituted or unsubstituted phenyl or naphthyl group; (b) ionic salts of the general formula $[A^+][BR^{**}4^-]$, where A^+ is a cationic Lewis or Bronsted acid capable of abstracting an alkyl, halogen, or hydrogen from the metallocene catalysts, B is boron, and R^{**} is a substituted

-26-


aromatic hydrocarbon, preferably a perfluorophenyl radical; (c) boron alkyls of the general formula $BR^{**}3$, where R^{**} is as defined above; or mixtures thereof. The activating cocatalyst may also be an organoaluminum compound, such as triisobutylaluminum or diethylaluminum chloride.

Preferably, the activating cocatalyst is a branched or cyclic oligomeric poly(hydrocarbylaluminum oxide) or a boron alkyl. More preferably, the activating cocatalyst is an aluminoxane such as methylaluminoxane (MAO) or modified methylaluminoxane (MMAO), or a boron alkyl.

Aluminoxanes are well known in the art and comprise oligomeric linear alkyl aluminoxanes represented by the formula:



and oligomeric cyclic alkyl aluminoxanes of the formula:



wherein s is 1-40, preferably 10-20; p is 3-40, preferably 3-20; and R^{***} is an alkyl group containing 1 to 12 carbon atoms, preferably methyl.

Aluminoxanes may be prepared in a variety of ways. Generally, a mixture of linear and cyclic aluminoxanes is obtained in the preparation of aluminoxanes from, for example, trimethylaluminum

-27-

and water. For example, an aluminum alkyl may be treated with water in the form of a moist solvent. Alternatively, an aluminum alkyl, such as trimethylaluminum, may be contacted with a hydrated salt, such as hydrated ferrous sulfate. The latter method comprises treating a dilute solution of trimethylaluminum in, for example, toluene with a suspension of ferrous sulfate heptahydrate. It is also possible to form methylaluminoxanes by the reaction of a tetraalkyldialuminoxane containing C₂ or higher alkyl groups with an amount of trimethylaluminum that is less than a stoichiometric excess. The synthesis of methylaluminoxanes may also be achieved by the reaction of a trialkyl aluminum compound or a tetraalkyldialuminoxane containing C₂ or higher alkyl groups with water to form a polyalkyl aluminoxane, which is then reacted with trimethylaluminum. Further modified methylaluminoxanes, which contain both methyl groups and higher alkyl groups, i.e., isobutyl groups, may be synthesized by the reaction of a polyalkyl aluminoxane containing C₂ or higher alkyl groups with trimethylaluminum and then with water as disclosed in, for example, U.S. Patent No. 5,041,584.

When the activating cocatalyst is a branched or cyclic oligomeric poly(hydrocarbylaluminum oxide), the mole ratio of aluminum atoms contained in the poly(hydrocarbylaluminum oxide) to total metal atoms contained in the catalyst precursor is generally in the range of from about 2:1 to about 100,000:1, preferably in the range of from about 10:1 to about 10,000:1, and most preferably in the range of from about 50:1 to about 2,000:1. When the activating cocatalyst is an ionic salt of the formula [A⁺][BR^{**}₄⁻] or a boron alkyl of the formula BR^{**}₃, the mole ratio of boron atoms contained in the ionic salt or the boron alkyl to total metal atoms contained in the catalyst precursor is

-28-

generally in the range of from about 0.5:1 to about 10:1, preferably in the range of from about 1:1 to about 5:1.

The catalyst precursor, the activating cocatalyst, or the entire catalyst composition may be impregnated onto a solid, inert support, in liquid form such as a solution, dispersion or neat liquid, spray dried, in the form of a prepolymer, or formed in-situ during polymerization. Particularly preferred among these is a catalyst composition that is spray dried as described in European Patent Application No. 0 668 295 A1 or in liquid form as described in U.S. Patent No. 5,317,036.

In the case of a supported catalyst composition, the catalyst composition may be impregnated in or deposited on the surface of an inert substrate such as silica, carbon black, polyethylene, polycarbonate porous crosslinked polystyrene, porous crosslinked polypropylene, alumina, thoria, zirconia, or magnesium halide (e.g., magnesium dichloride), such that the catalyst composition is between 0.1 and 90 percent by weight of the total weight of the catalyst composition and the support.

The catalyst composition may be used for the polymerization of olefins by any suspension, solution, slurry, or gas phase process, using known equipment and reaction conditions, and is not limited to any specific type of reaction system. Generally, olefin polymerization temperatures range from about 0°C to about 200°C at atmospheric, subatmospheric, or superatmospheric pressures. Slurry or solution polymerization processes may utilize subatmospheric or superatmospheric pressures and temperatures in the range of about 40°C to about 110°C. A useful liquid phase polymerization reaction system is described in U.S. Patent 3,324,095. Liquid phase reaction systems generally comprise a reactor vessel to which olefin monomer and catalyst composition are added, and which contains a liquid

-29-

reaction medium for dissolving or suspending the polyolefin. The liquid reaction medium may consist of the bulk liquid monomer or an inert liquid hydrocarbon that is nonreactive under the polymerization conditions employed. Although such an inert liquid hydrocarbon need not function as a solvent for the catalyst composition or the polymer obtained by the process, it usually serves as solvent for the monomers employed in the polymerization. Among the inert liquid hydrocarbons suitable for this purpose are isopentane, hexane, cyclohexane, heptane, benzene, toluene, and the like. Reactive contact between the olefin monomer and the catalyst composition should be maintained by constant stirring or agitation. The reaction medium containing the olefin polymer product and unreacted olefin monomer is withdrawn from the reactor continuously. The olefin polymer product is separated, and the unreacted olefin monomer and liquid reaction medium are recycled into the reactor.

Preferably, gas phase polymerization is employed, with superatmospheric pressures in the range of 1 to 1000 psi, preferably 50 to 400 psi, most preferably 100 to 300 psi, and temperatures in the range of 30 to 130°C, preferably 65 to 110°C. Stirred or fluidized bed gas phase reaction systems are particularly useful. Generally, a conventional gas phase, fluidized bed process is conducted by passing a stream containing one or more olefin monomers continuously through a fluidized bed reactor under reaction conditions and in the presence of catalyst composition at a velocity sufficient to maintain a bed of solid particles in a suspended condition. A stream containing unreacted monomer is withdrawn from the reactor continuously, compressed, cooled, optionally fully or partially condensed as disclosed in U.S. Patent Nos. 4,528,790 and 5,462,999, and recycled to the reactor. Product is withdrawn from the reactor and make-up monomer is added

-30-

to the recycle stream. As desired for temperature control of the system, any gas inert to the catalyst composition and reactants may also be present in the gas stream. In addition, a fluidization aid such as carbon black, silica, clay, or talc may be used, as disclosed in U.S. Patent No. 4,994,534.

Polymerization may be carried out in a single reactor or in two or more reactors in series, and is conducted substantially in the absence of catalyst poisons. Organometallic compounds may be employed as scavenging agents for poisons to increase the catalyst activity. Examples of scavenging agents are metal alkyls, preferably aluminum alkyls, most preferably triisobutylaluminum.

Conventional adjuvants may be included in the process, provided they do not interfere with the operation of the catalyst composition in forming the desired polyolefin. Hydrogen or a metal or non-metal hydride, e.g., a silyl hydride, may be used as a chain transfer agent in the process. Hydrogen may be used in amounts up to about 10 moles of hydrogen per mole of total monomer feed.

Olefin polymers that may be produced according to the invention include, but are not limited to, ethylene homopolymers, homopolymers of linear or branched higher alpha-olefins containing 3 to about 20 carbon atoms, and interpolymers of ethylene and such higher alpha-olefins, with densities ranging from about 0.86 to about 0.96. Suitable higher alpha-olefins include, for example, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, and 3,5,5-trimethyl-1-hexene. Olefin polymers according to the invention may also be based on or contain conjugated or non-conjugated dienes, such as linear, branched, or cyclic hydrocarbon dienes having from about 4 to about 20, preferably 4 to 12, carbon atoms. Preferred dienes include 1,4-pentadiene, 1,5-hexadiene, 5-vinyl-2-norbornene, 1,7-octadiene,

-31-

vinyl cyclohexene, dicyclopentadiene, butadiene, isobutylene, isoprene, ethylidene norbornene and the like. Aromatic compounds having vinyl unsaturation such as styrene and substituted styrenes, and polar vinyl monomers such as acrylonitrile, maleic acid esters, vinyl acetate, acrylate esters, methacrylate esters, vinyl trialkyl silanes and the like may be polymerized according to the invention as well. Specific olefin polymers that may be made according to the invention include, for example, polyethylene, polypropylene, ethylene/propylene rubbers (EPR's), ethylene/propylene/diene terpolymers (EPDM's), polybutadiene, polyisoprene and the like.

The following examples further illustrate the invention.

EXAMPLES

Glossary

Activity is measured in g polyethylene/mmol metal·hr·100 psi ethylene.

I2 is melt index (dg/min), measured using ASTM D-1238 Condition E at 190° C.

I21 is flow index (dg/min), measured using ASTM D-1238-Condition F.

MFR is Melt Flow Ratio, I21/I2.

BBF is Butyl Branching Frequency, number of butyl branches per 1000 main chain carbon atoms based on infrared measurement techniques.


-32-

M_n is Number Average Molecular Weight, as determined by gel permeation chromatography using crosslinked polystyrene columns; pore size sequence: 1 column less than 1000 Å, 3 columns of mixed 5×10^7 Å; 1,2,4-trichlorobenzene solvent at 140° C with refractive index detection.

PDI is Polydispersity Index, equivalent to Molecular Weight Distribution (M_w/M_n).

EXAMPLE 1

Preparation of 2-Acetylpyridine [2,6-Diisopropylphenylimine] Ligand



Into a 50 mL round bottom flask equipped with a stir bar and septa was charged 11.0 mmol 2,6-diisopropylaniline and 9.5 mmol 2-acetylpyridine. With vigorous stirring, 0.5 mmol 2-acetylpyridine-HCl was added. The reaction vessel was placed under a strong nitrogen purge and was vented to a trap. The reaction was heated to 160° C for 2 hours. The reaction vessel was allowed to cool to room temperature. 10 mL hexane was added and stirred vigorously, then allowed to settle overnight. The mixture was filtered and the filtrate was vacuum stripped to obtain the yellow solid product with a melting point of 68-70° C.

-33-

EXAMPLE 2Preparation of [2-Pyridyl(Me)(PhCH₂)C(N-2,6-Diisopropyl-phenyl)]Zr(PhCH₂)₃

In a darkened dry box in a darkened room 0.5 mmol (0.14g) of the ligand of Example 1 was charged to an oven-dried 50 mL round-bottom flask equipped with a stir bar and containing 0.5 mmol (0.23g) tetrabenzyl zirconium. With vigorous stirring, 7.5 mL benzene-d₆ was added to prepare a 0.067M solution. The reaction vessel was immediately covered with foil and the solution was allowed to stir in the dry box overnight.

EXAMPLE 3Preparation of [2-Pyridyl(Me)(PhCH₂)C(N-2,6-Diisopropyl-phenyl)]Zr(PhCH₂)₃

In a dry box, 50 mmol (11.65g) ZrCl₄ was charged to a 300 mL Schlenk flask equipped with a stir bar. Into a 100 mL Schlenk flask equipped with a stir bar was charged 50 mmol (14.02g) of the ligand of Example 1. To both flasks was added 100 mL of dry toluene. Both flasks were sealed with septa and allowed to stir. When the ligand was dissolved, the solution was transferred slowly via syringe into the vigorously stirring ZrCl₄ slurry. The pale yellow mixture was allowed to stir overnight in the dry box.

While the ligand/ ZrCl₄ mixture was stirring, preparation of a Grignard solution was started. Two hundred mmol (200 mL) of benzylmagnesium chloride (1.0 M solution in diethyl ether) was charged via syringe to an oven-dried 500 mL Schlenk flask equipped with a stir bar and sealed with a septum. The ether was stripped

-34-

under high vacuum (0.2 Torr). The vessel was taken into the dry box where 100 mL dry toluene was added to the residue. The residue was dissolved and removed from the dry box, placed on the high vacuum manifold, and stripped again. This procedure was repeated three additional times, until the residue was no longer a viscous reddish liquid, but an off-white powder. When the powder stage was reached 100 mL of dry toluene was added and the solids dissolved. The vessel was removed from the dry box and placed under argon.

After stirring overnight, the ligand/ ZrCl_4 mixture was bright yellow. The vessel was removed from the dry box and placed under argon beside the vessel containing the Grignard solution. The ligand/ ZrCl_4 solution was covered with foil and chilled to -78°C . In the darkened room the Grignard solution was slowly transferred via double-ended cannula into the ligand/ ZrCl_4 solution. The reaction mixture turned bright red when the addition was complete. The reaction was allowed to slowly warm to room temperature. After stirring for a few hours the vessel was returned to the dry box and filtered through a medium porosity frit. Toluene was added to the filtrate to adjust the volume to 500 mL. The filtrate was transferred to an amber bottle. A 1.0 mL subsample was removed and placed in a tared 10 mL flask. The subsample was vacuum stripped and the mass of the residue was used to determine the molarity of the solution at 0.089M.

Preparation of 1 liter of 0.02M solution was accomplished using 224.7 mL of catalyst solution and diluting to 1000 mL with dry toluene.

-35-

EXAMPLE 4

A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using a catalyst composition comprising the catalyst precursor of Example 2 with modified methylaluminoxane, MMAO (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.).

In each case, the catalyst composition was prepared by combining a solution of the catalyst precursor of Example 2 in benzene with the MMAO solution in the presence of 0.1 mL 1-hexene. Reaction conditions and results are shown in Table 1 below.

TABLE 1

Example	Hexene mL	MMAO/Zr Mole Ratio	T, °C	C ₂ psi	Activity	BBF
4a	43	1000	65°C	85	115K	7.16
4b	43	1000	75°C	85	80.6K	10.34
4c	43	1000	85°C	85	49.1K	9.71
4d	43	1000	65°C	170	101K	2.41
4e	43	1000	92.9K	170	92.9K	4.95
4f	43	1000	85°C	170	61.8K	2.37
4g	21.5	1000	75°C	85	8.1K	3.16
4h	43	1000	75°C	85	80.6K	10.34
4i	86	1000	75°C	85	95.6K	17.99
4j	43	2000	65°C	85	210K	7.30
4k	43	1000	65°C	85	115K	7.16
4l	43	500	65°C	85	4.6K	9.22

EXAMPLE 5




A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using catalyst compositions comprising various catalyst precursors according to the invention with MMAO cocatalyst.

In each case, the catalyst composition was prepared by contacting the ligand shown below in Table 2 with tetrabenzyl

-36-





zirconium, dissolving the resulting material in toluene, and then contacting with MMAO solution (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.) in the presence of 0.1 mL 1-hexene. Polymerization reactions were carried out at 65° C, 85 psi ethylene, 1.0 micromole Zr, and a MMAO/Zr mole ratio of 1,000. Ligands and results are shown in Table 2 below.

TABLE 2

<u>Example</u>	<u>Ligand</u>	<u>Activity</u>	<u>I21</u>	<u>BBF</u>
5a		25647	9.83	10.51
5b		24,941	0.897	4.37
5c		5,647		






-37-

TABLE 2

<u>Example</u>	<u>Ligand</u>	<u>Activity</u>	<u>I21</u>	<u>BBF</u>
5d		2,353		
5e		23,294	0.511	9.23
5f		68,235	too slow for meas- urement	6.85
5g		10,118		5.86



-38-

TABLE 2

<u>Example</u>	<u>Ligand</u>	<u>Activity</u>	<u>I21</u>	<u>BBF</u>
5h		39,059	1.04	12.49
5i		22,824	5.39	13.64
5j		15,765		5.96
5k		40,941	2.42	13.36
5l		183,059	too slow for measure- ment	8.68

-39-

TABLE 2

<u>Example</u>	<u>Ligand</u>	<u>Activity</u>	<u>I21</u>	<u>BBF</u>
5m		4706		
5n		941		





EXAMPLE 6

A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using mixed catalyst compositions according to the invention with MMAO cocatalyst.

In each case, the catalyst composition was prepared by contacting mixtures of the ligands shown below in Table 3 with tetrabenzyl zirconium, dissolving the resulting material in toluene, and then contacting with MMAO solution (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.) in the presence of 0.1 mL 1-hexene. Polymerization reaction conditions were 65° C, 85 psi ethylene, 1.0 micromole Zr, and a MMAO/Zr mole ratio of 1,000. Ligands and results are shown in Table 3 below.

-40-

TABLE 3

<u>Example</u>	<u>Ligands</u>	<u>Activity</u>	<u>BBF</u>
6a	<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>1 eq.</p> </div> <div style="text-align: center;">  <p>1 eq.</p> </div> </div>	46,588	8.64
6b	<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>2 eq.</p> </div> <div style="text-align: center;">  <p>1 eq.</p> </div> </div>	109,176	7.90

EXAMPLE 7

An ethylene/hexene copolymer was made in a laboratory scale, slurry phase reactor using a mixed catalyst composition comprising the catalyst precursor of Example 2, biscyclopentadienyl zirconium dichloride, and MMAO.

Polymerization reaction conditions were 65° C, 85 psi ethylene, 1.0 micromole Zr, and a MMAO/Zr mole ratio of 1,000. The activity of the catalyst composition was 20,706. Polyethylene copolymer having an I21 of 1.74 was made.

-41-

EXAMPLE 8

The catalyst precursor of Example 3 combined with MMAO was used as the catalyst composition to polymerize an ethylene/1-hexene copolymer (density 0.917, melt index 1.0) in a pilot-scale, fluidized bed, gas phase reactor. The reactor was nominally 1 foot in diameter and was operated with a bed height of 8 feet and a superficial gas velocity of approximately 1.8 ft/sec. Total reactor pressure was 350 psig.

A seed bed was charged to the reactor and it was dried to <5 ppm water. The reactor was pressurized to 200 psig of ethylene. The 1-hexene/ethylene and hydrogen/ethylene mole ratio was established at 0.048 and 0.041. The bed temperature was adjusted to 70° C.


The catalyst composition was employed in liquid form. The catalyst composition was made by mixing the catalyst precursor of Example 3 in toluene with MMAO (2.8 wt % Al, commercially available from Akzo Chemicals, Inc.). Additional dilution of the catalyst composition was performed by adding isopentane to the mixture. The catalyst composition sprayed into the reactor with the aid of 5.0-7.0 lb/hr of nitrogen gas and a stream of 1950 lbs/hr of recycle gas.

Reactor static was clearly absent throughout the run. The expanded section, recycle line and distributor plate were free from fouling. The average particle size (APS) held steady and could be controlled by varying the nitrogen carrier flow and resin density.

EXAMPLE 9

-42-

Preparation Of [1-(2-Pyridyl)N-1-Methylethyl][1-N-2,6-Diisopropylphenyl]Amine



In a dry box, 22.45 mmol (6.34 g) 2-acetylpyridine(2,6-diisopropylphenylimine) were charged to a 250 mL round bottom flask equipped with a stir bar and septa. The flask was sealed, removed from the dry box and placed under nitrogen purge. Dry toluene (50 mL) was added and stirred to dissolve the ligand. The vessel was chilled to 0° C in a wet ice bath. Trimethyl aluminum (Aldrich, 2.0 M in toluene) was added dropwise over ten minutes. The temperature of the reaction was not allowed to exceed 10° C. When addition of the trimethyl aluminum was complete, the mixture was allowed to warm slowly to room temperature, and then was then placed in an oil bath and heated to 40° C for 25 minutes. The vessel was removed from the oil bath and placed in an ice bath. A dropping funnel containing 100 mL of 5% KOH was attached to the flask. The caustic was charged to the reaction dropwise over a 1 hour span. The mixture was transferred to a separatory funnel. The aqueous layer was removed. The solvent layer was washed with 100 mL water then 100 mL brine. The red-brown liquid product was dried over Na₂SO₄, vacuum stripped and placed under high vacuum over night.

80 mL of red-brown liquid was transferred to a 200 mL Schlenk flask equipped with a stir bar. A distillation head with a dry ice condenser was attached to the flask. The mixture was vacuum distilled yielding approximately 70 g of dark yellow viscous liquid product.

EXAMPLE 10

A series of catalyst precursors according to the invention were made using the ligand of Example 9 and a variety of metal compounds. Each catalyst precursor was made by first combining the ligand in ether with methyllithium and then contacting the resulting product with the metal compound shown in Table 4 below. The resulting catalyst precursors were combined with a cocatalyst and used for the slurry homopolymerization of ethylene in a laboratory scale reactor in the manner described in Example 4.

The results are shown in Table 4.

TABLE 4

<u>Example</u>	<u>Metal Compound</u>	<u>Cocatalyst</u>	<u>g PE</u>
9a	ZrCl ₄	MMAO	0.484
9b	Cr(THF) ₃ Cl ₃	MMAO	0.239
9c	V(THF) ₃ Cl ₃	MMAO	0.158
9d	SmCl ₃	MMAO	0.797
9e	YCl ₃	MMAO	0.935
9f	TaCl ₅	MMAO	0.195
9g	NbCl ₅	MMAO	0.185
9h	SmCl ₃	TIBA(100eq)	0.024
9i	YCl ₃	TIBA(100eq)	0.053
9j	ZrCl ₄	TIBA(100eq)	0.024
9k	V(THF) ₃ Cl ₃	TIBA(100eq)	0.022
9l	Cr(THF) ₃ Cl ₃	TIBA(100eq)	0.037
9m	NbCl ₅	TIBA(100eq)	0.032
9n	TaCl ₅	TIBA(100eq)	0.024
9o	V(THF) ₃ Cl ₃	DEAC(100eq)	0.090
9p	Cr(THF) ₃ Cl ₃	IBAO(100eq)	0.134

EXAMPLE 11

-44-

Preparation Of [1-(2-Pyridyl)N-1-Methylethyl][1-N-2,6-Diisopropylphenyl Amido] Zirconium Tribenzyl

In a darkened room and darkened dry box, 5.0 mmol (1.45 g) of the ligand made in Example 10 were charged to a 100 mL Schlenk tube equipped with a stir bar. The ligand was dissolved in 5 mL of toluene. To a second vessel equipped with a stir bar was charged 5.5 mmol (2.5g) tetrabenzyl zirconium and 10 mL toluene.

The ligand solution was transferred into the tetrabenzyl zirconium solution. The vessel was covered with foil and allowed to stir at room temperature in the dry box. After 6 hours at room temperature 80 mL dry hexane was added to the reaction solution and allowed to stir overnight. The reaction mixture was filtered through a medium porosity frit with approximately 2g pale yellow solids collected.

EXAMPLE 12

Preparation Of [[1-(2-Pyridyl)N-1-Methylethyl]-[1-N-2,6-Diisopropylphenyl Amido]][2-Methyl-1-Phenyl-2-Propoxy] Zirconium Dibenzyl

To an oven-dried, cooled, purged and sealed GC vial was charged 0.10 mL dried acetone. The GC vial was sealed in a shell vial and taken into the dry box. In a darkened room and darkened dry box 2.0 mmol (1.3g) of the material made in Example 11 and 9 mL toluene were charged to a 100 mL Schlenk flask equipped with a stir bar. To a second GC vial was charged 2.0 mmol (146 uL) acetone and 1.0 mL toluene. The acetone/toluene solution was transferred dropwise via syringe into the stirred solution of [1-(2pyridyl) N-1-methylethyl][1-N-2,6-diisopropylphenylamido] zirconium tribenzyl. The vessel was

-45-

covered with foil and allowed to stir at room temperature in the dry box overnight.

The reaction solution was vacuum stripped to a tacky orange residue. Dry hexane (20 mL) was added and the residue stirred vigorously, then vacuum stripped again to a yellow-orange glass. Hexane was added again and vigorously stirred. The vessel was placed in a freezer (-24° C) for approximately 2 hours. The mixture was filtered through a medium porosity frit. Pale yellow solids (0.8 g) were collected.

EXAMPLE 13

Hexane (600mL), triisobutylaluminum (100 μ moles of a 1.0M solution in toluene) and 1-hexene (43 mls, alumina dried) were charged to a 1 liter slurry reactor.

The complex from Example 11 (2.46 μ moles) and trityl(tetraphenyl)borate (2.33 μ moles) were weighed into an oven dried, glass vial. Toluene (1.0 ml) was added and the mixture was stirred for 5 minutes resulting in a yellow solution. Triisobutylaluminum (10 μ moles of a 1.0M solution in toluene) was added to the solution to make a reaction solution. An aliquot of the reaction solution (0.20 mls, 0.5 μ moles Zr) was charged to the reactor 4 minutes after the triisobutylaluminum addition and the reaction was started. The reactor was run at 75°C and 85 psia ethylene pressure for 30 minutes.

The polyethylene resin produced weighed 76.5g. The calculated activity was 360000 g/ mmole Zr/ 100psi ethylene/ hour. The molecular weight of the resin was too high to obtain an I21 or I2.

-46-

EXAMPLE 14

Hexane (600mL), triisobutylaluminum (100 μ moles of a 1.0M solution in toluene) and 1-hexene (43 mls, alumina dried) were charged to a 1 liter slurry reactor

Trityl(tetraphenyl)borate (1.89 μ moles, Akzo) was weighed into an oven dried, glass vial. Toluene (1.0 ml) was added resulting in a dark yellow solution. The complex described in Example 12, (2.0 μ moles, 0.025 mls of an 80 μ mole/ml solution in deuterated benzene) was added to the dark yellow solution resulting in an immediate pale yellow solution. After 5 minutes of stirring triisobutylaluminum (10 μ moles of a 1.0M solution in toluene) was added to the solution to make a reaction solution. An aliquot of the reaction solution (0.25 mls, 0.5 μ moles Zr) was charged to the reactor 2 minutes after the triisobutylaluminum addition the reaction was started. The reactor was operated at 75°C and 85 psia ethylene pressure for 30 minutes. The product weighed 16.8g. The activity was 79059 g/ mmole Zr/ 100psi ethylene/ hour. The resin was treated with ~1000 ppm anti-oxidant (4 parts Irgafos®168, 1part Irganox® 1076) & 3g was loaded into a Tinius Olsen extrusion plastometer. The resin extruded through the plastometer under the weight of the plunger (100g). I2 data was therefore not obtained, but the quick extrusion indicates a low molecular weight product. A 3 mil plaque was made of the treated resin which was analyzed on an FTIR giving a butyl branch frequency of 8.04/ 1000 CH₂.

EXAMPLE 15

In each of Examples 15a-15f, in a darkened dry box and darkened room, 0.100 mmol of [1-(2-pyridyl)N-1-methylethyl][1-N-2,6-diisopropylphenylamido] zirconium tribenzyl was dissolved in 1.0 mL



-47-

of benzene-d₆ in a 10 mL Schlenk flask. To a second vessel was charged 0.100 mmol of the desired reactant described in Table 5 and 0.5 mL benzene-d₆. The second solution was transferred into the first solution dropwise. The vessel was sealed, covered with foil and allowed to stir overnight. The resultant solutions were analyzed by ¹H-nmr to determine the conversion of [1-(2-pyridyl)N-1-methylethyl][1-N-2,6-diisopropylphenylamido] zirconium tribenzyl to the products described in Table 5.

A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using products described in Table 5 with MMAO (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.). In each case, the catalyst composition was prepared by combining a benzene solution of the product described in Table 5 with the MMAO solution in the presence of 0.1 mL 1-hexene. Reaction conditions were 85° C, 85 psi ethylene, 0.5 micro moles of zirconium complex, 43mL 1-hexene, and 1000 equivalents of MMAO per zirconium. The results are shown in Table 5.

-48-

TABLE 5

Example	Product	Reactant	Conversion	Activity	I ₂ I	BBE
15a		Acetophenone	~100%	87,059	too slow for measurement	12.97
15b		Benzaldehyde	~100%	101,647	0.235	10.48


17731-PC

SUBSTITUTE SHEET (RULE 28)

TABLE 5

Reactant	Conversion	Activity	I21	BBF
Piperidine	~83%	96,941	0.141	6.71

Product





15c

Example

17731-PC

-50-

TABLE 5

Example	Product	Reactant	Conversion	Activity	I ₂₁	BBF
15d		Morpholine	~94%	148,235	0.292	20.48
15e		Phenol	~90%	189,176	too slow for measurement	10.19

17731-PC

SUBSTITUTE SHEET (RULE 26)

EXAMPLE 16Preparation Of [1-(2-Pyridyl)-N-Ethenyl-(2,6-Diisopropyl-phenylamido)] Zirconium Tribenzyl

In a dry box 10 mmol (2.80g) 2-acetylpyridine(2,6-diisopropylphenylimine) was charged to 100 mL Schlenk flask equipped with a stir bar and sealed with a septa. The flask was removed from the dry box and placed under argon. Twenty mL tetrahydrofuran was added to the ligand and stirred to dissolve. The solution was chilled to -70°C and 10 mmol (7.1 mL) methyl lithium (Aldrich, 1.4 M solution in ether) was added dropwise. The clear red-orange mixture was allowed to slowly warm to room temperature. The mixture thickened as it warmed. An additional 20 mL THF was added. After stirring at room temperature for 4 hours, the mixture was again chilled to -70°C and 10 mmol (1.27 mL) chlorotrimethylsilane (Aldrich) was added dropwise to the ligand/methyl lithium mixture. The red-orange mixture was allowed to slowly warm to room temperature and stir overnight.

The reaction mixture was vacuum stripped to a powdery, pale yellow residue which was taken into the dry box.

The resulting ligand was dissolved in 20 mL toluene. In a second flask 10 mmol (2.33g) of zirconium (IV) chloride was slurried in 10 mL toluene. The ligand solution was added to the $ZrCl_4$ slurry with vigorous stirring. The yellow slurry was allowed to stir overnight in the dry box.

The slurry was removed from the dry box, vacuum stripped and 20 mL toluene added to the residue. In a second 100 mL Schlenk flask was charged 30 mmol (30 mL) benzylmagnesium chloride (Aldrich, 1.0 M solution in ether). The solution was vacuum stripped and the

-52-

solvent replaced with toluene. Repeating the wash 3 times resulted in a powdery off-white residue which was dissolved in 20 ml toluene.

In a darkened lab and hood the benzylmagnesium chloride solution was cannula transferred into the chilled (-70°C) ligand/ ZrCl_4 slurry. The vessel was covered with foil and allow to slowly warm to room temperature and stir over night. The reaction mixture was taken into the dry box and filtered through a medium porosity frit. The solids were washed with toluene then discarded. The filtrate was transferred into an amber bottle.

EXAMPLE 17

A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using a catalyst composition comprising the catalyst precursor of Example 17 with MMAO (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.).


In each case, the catalyst composition was prepared by combining a solution of the catalyst precursor of Example 17 in benzene with the MMAO solution in the presence of 0.1 mL 1-hexene. Reaction conditions and results are shown in Table 6 below.

D-17731

TABLE 6

Example	C ₆ mL	T.C	C ₂ psi	gPE	Activity	I ₂	MFR	Mn	PDI	BBF
17a	43	65	85	27.7	28,000	.512	44.21	24,120	4.707	12.26
17b	86	65	170	42.4	30,235	NF	NF	-	-	15.06
17c	43	75	85	12.1	26,118	.577	27.56	13,944	5.896	14.46
17d	86	75	170	32.6	17,765	.09	34.52	51,382	3.779	12.09
17e	43	85	85	9.7	14,588	1.138	31.38	31,332	3.367	9.13
17f	86	85	170	25.3	14,118	.208	29.13	45,632	3.524	11.23


-54-

EXAMPLE 18Preparation Of N-Tetrahydrofurfuryl[N-2,6-Diisopropylphenyl]Amine

2,6-Diisopropyl aniline (50 mmol, 8.86g Aldrich, 90%) was charged to an oven-dried, cooled Schlenk flask equipped with a stir bar and septa. The flask was placed under a nitrogen purge and 20 mL of dry tetrahydrofuran was added. The flask was chilled to 0° C and n-butyl lithium (50 mmol, 17.8 mL, Aldrich, 2.81M solution in hexane) was added dropwise via syringe. The mixture was allowed to slowly warm to room temperature.

Tetrahydrofurfuryl chloride (50 mmol, 5.4 mL, Aldrich, 98%) was added via syringe and the mixture was heated at 50° C overnight. The reaction solution was cooled to ambient temperature and hydrolyzed. The aqueous layer was extracted 3 times with ether. The organics were combined and vacuum stripped. The residue was vacuum distilled using a shortpath distillation column. The product distillate (140-144° C, 0.25 torr, 4 grams) was a clear yellow liquid.

-55-

EXAMPLE 19**Preparation Of [N-Tetrahydrofurfuryl][N-2,6-Diisopropylphenylamido] Zirconium Tribenzyl**

Tetrabenzyl zirconium (0.200 mmol, 0.091g) was charged to a 7 mL amber bottle equipped with a stir bar and screw-cap. Dried benzene-d₆ (2 mL) was added and stirred to dissolve. To a second vial was charged the ligand made in Example 18 (0.200 mmol, 0.052g,) and dried benzene-d₆ (1.0 mL). The N-tetrahydrofurfuryl[N-2,6-diisopropylphenylimine] solution was transferred into the stirred tetrabenzyl zirconium solution. The bottle was capped and the reaction solution was allowed to stir overnight.

EXAMPLE 20

A series of ethylene/hexene copolymers were made in a laboratory scale, slurry phase reactor using a catalyst composition comprising the catalyst precursor of Example 19 with MMAO (7.0 wt % Al in heptane, commercially available from Akzo Chemicals, Inc.).

In each case, the catalyst composition was prepared by combining a solution of the catalyst precursor in benzene with the

-56-

MMAO solution in the presence of 0.1 mL 1-hexene.

Polymerization reactions were carried out at 85 psi ethylene, 0.5 micromole Zr, and a MMAO/Zr mole ratio of 1,000. Reaction conditions and results are shown in Table 7 below.

TABLE 7


<u>Example</u>	<u>C₆mL</u>	<u>T.C</u>	<u>C₂ psi</u>	<u>Activity</u>	<u>I21</u>	<u>BBF</u>
20a	43	65	85	35,765	NF	9.82
20b	43	75	85	20,235	.114	9.77
20c	43	85	85	13,176	-	-

I claim:

1. A catalyst precursor having the formula:



wherein each A has the formula:



M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements;

each L is a monovalent, bivalent, or trivalent anion;

X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R¹ is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R¹ groups may be joined to form a cyclic moiety;

each R² is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R² groups may be joined to form a cyclic moiety;

Q is a bridging group;




each m is independently an integer from 0 to 5;

n is an integer from 1 to 4;

q is 1 or 2;


and when q is 2, the A groups are optionally connected by a bridging group Z.

2. The catalyst precursor of claim 1, having a formula selected from the group consisting of:



and



-59-




wherein R_a and R_b are each independently selected from the group consisting of alkyl, aryl, heterocyclic groups, and hydrogen and R_a and R_b can be optionally connected to form a ring; R_c and R_d are each independently selected from the group consisting of alkyl, aryl, and hydrogen; and each L is a monovalent, bivalent, or trivalent anion.

-60-

3. A catalyst precursor having a formula selected from the group consisting of:



and




4. A catalyst composition comprising:

a) a catalyst precursor having the formula



wherein each A has the formula:



M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements;

each L is a monovalent, bivalent, or trivalent anion;

X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group;

each m is independently an integer from 0 to 5;

n is an integer from 1 to 4;




q is 1 or 2;

and when q is 2, the A groups are optionally connected by a bridging group Z; and


-62-

b) an activating cocatalyst.

5. The catalyst composition of claim 4, wherein the catalyst precursor has a formula selected from the group consisting of:





and




wherein R_a and R_b are each independently selected from the group consisting of alkyl, aryl, heterocyclic groups, and hydrogen and R_a and R_b can be optionally connected to form a ring; R_c and R_d are each independently selected from the group consisting of alkyl, aryl, and hydrogen; and each L is a monovalent, bivalent, or trivalent anion.

6. The catalyst composition of claim 4, wherein the catalyst precursor has a formula selected from the group consisting of:



and

-64-




7. A process for the polymerization of olefins, which comprises contacting olefin under polymerization conditions with a catalyst composition comprising:

a) a catalyst precursor having the formula



wherein each A has the formula:



M is a metal selected from the group consisting of Group 3 to 13 elements and Lanthanide series elements;

each L is a monovalent, bivalent, or trivalent anion;

X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17

elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is independently a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group;

each m is independently an integer from 0 to 5;



n is an integer from 1 to 4;

q is 1 or 2;


and when q is 2, the A groups are optionally connected by a bridging group Z; and

b) an activating cocatalyst.


8. The process of claim 7, wherein the catalyst precursor has a formula selected from the group consisting of:



-66-





and




wherein R_a and R_b are each independently selected from the group consisting of alkyl, aryl, heterocyclic groups, and hydrogen and R_a and R_b can be optionally connected to form a ring; R_c and R_d are each independently selected from the group consisting of alkyl, aryl, and hydrogen; and each L is a monovalent, bivalent, or trivalent anion.

-67-

9. The process of claim 7, wherein the catalyst precursor has a formula selected from the group consisting of:




and



-68-

10. A catalyst precursor comprising the reaction product of an organometal compound and a heteroatom-containing ligand having a formula selected from the group consisting of:



wherein X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;


each R^2 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group; and

each m is independently an integer from 0 to 5.

11. The catalyst precursor of claim 10, wherein the organometal compound is a zirconium hydrocarbyl and the heteroatom-containing ligand is a pyridine/imine ligand of the formula:

-69-



wherein each R' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R' groups may be joined to form an aliphatic or aromatic ring;

each R'' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R'' groups may be joined to form an aliphatic or aromatic ring;


R³ is hydrogen, a hydrocarbon group containing 1 to 20 carbon atoms optionally substituted with one or more heteroatoms, or a heteroatom optionally substituted with a hydrocarbon group; and

each m is independently an integer from 0 to 5.

12. A catalyst composition comprising:

a) a catalyst precursor that is the reaction product of an organometal compound and a heteroatom-containing ligand having a formula selected from the group consisting of:

-70-



wherein X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group; and


each m is independently an integer from 0 to 5;

and

b) an activating cocatalyst.

13. The catalyst composition of claim 12, wherein the catalyst precursor comprises the reaction product of a zirconium hydrocarbyl and a pyridine/imine ligand of the formula:

-71-



wherein each R' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R' groups may be joined to form an aliphatic or aromatic ring;

each R'' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R'' groups may be joined to form an aliphatic or aromatic ring;


R³ is hydrogen, a hydrocarbon group containing 1 to 20 carbon atoms optionally substituted with one or more heteroatoms, or a heteroatom optionally substituted with a hydrocarbon group; and

each m is independently an integer from 0 to 5.

14. A process for the polymerization of olefins, which comprises contacting olefin under polymerization conditions with a catalyst composition comprising:

a) a catalyst precursor that is the reaction product of an organometal compound and a heteroatom-containing ligand having a formula selected from the group consisting of:

-72-



wherein X and Y are each heteroatoms;

Cyclo is a cyclic moiety;

each R^1 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^1 groups may be joined to form a cyclic moiety;

each R^2 is a group containing 1 to 50 atoms selected from the group consisting of hydrogen and Group 13 to 17 elements, and two or more adjacent R^2 groups may be joined to form a cyclic moiety;

Q is a bridging group; and


each m is independently an integer from 0 to 5;

and

b) an activating cocatalyst.

15. The process of claim 14, wherein the catalyst precursor comprises the reaction product of a zirconium hydrocarbyl and pyridine/imine ligand of the formula.

-73-



wherein each R' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R' groups may be joined to form an aliphatic or aromatic ring;

each R'' is a hydrocarbon group containing 1 to 20 carbon atoms and two or more adjacent R'' groups may be joined to form an aliphatic or aromatic ring;

R^3 is hydrogen, a hydrocarbon group containing 1 to 20 carbon atoms optionally substituted with one or more heteroatoms, or a heteroatom optionally substituted with a hydrocarbon group; and

each m is independently an integer from 0 to 5.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 98/13781

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C07F7/00 C08F4/60 C08F10/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08F C07F		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	GIBSON V C ET AL: "Synthesis and structural characterisation of aluminium imino-amide and pyridyl-amide complexes: bulky monoanionic N,N chelate ligands via methyl group transfer" JOURNAL OF ORGANOMETALLIC CHEMISTRY, vol. 550, no. 1-2, 15 January 1998, page 453-456 XP004109893 see page 453, column 1, paragraph 1 - column 2, paragraph 1 see page 456, column 2, line 2	1,2,4,5, 7,8
P,Y	EP 0 803 520 A (BASF AG) 29 October 1997 see claims 1,2,7 --- -/--	1,2,4,5, 7,8
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search 22 October 1998		Date of mailing of the international search report 29/10/1998
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Fischer, B

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 98/13781

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	ORRELL K G ET AL: "Stereochemically non-rigid transition metal complexes of 2,6-bis(1-(phenylimino)ethyl)pyridine (BIP). Part 3. Dynamic NMR studies of fac-PtXMe3(BIP)! (X=Cl, Br, or I). Crystal structure of fac -PtI Me3(BIP)!" JOURNAL OF ORGANOMETALLIC CHEMISTRY, vol. 555, no. 1, 25 March 1998, page 35-47 XP004112400 see the whole document	1
A	WO 96 33202 A (OCCIDENTAL CHEM CO) 24 October 1996 cited in the application see claims 1,9	1

Form PCT/ISA210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 98/13781

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0803520 A	29-10-1997	DE 19616523 A JP 10036420 A	06-11-1997 10-02-1998
WO 9633202 A	24-10-1996	US 5637660 A AU 5314496 A EP 0832089 A	10-06-1997 07-11-1996 01-04-1998